

DIO INDOOR

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+11.25	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,12	75	14/16/18	INC
1.60	1.597	1.30	42	400	Clear	S+10.00	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	14/16/18	INM
1.67	1.665	1.35	32	400	Clear	S+11.50	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	14/16/18	INH
1.74	1.738	1.47	31	390	Clear	S+10.50	to	-12.00	0.75~3.50	0.5,1,5,3,5,5,6,7,8,5,10,25,12.5	75	14/16/18	INU
TVX	1.530	1.11	45	400	Clear	S+7.00	to	-10.50	0.75~3.50	0.5,1,2,2,5,3,4,5,6,7,8	75	14/16/18	INV
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to	-11.00	0.75~3.50	1,2,5,4,5,6,7,8,9,10,11	75	14/16/18	IN3
Polycarbonate	1.586	1.17	31	380	Clear		to		0.75~3.50		75	14/16/18	INP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	2,25,4,25,5,25,6,25,8,25	76	14/16/18	INA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+9.50	to	-11.00	0.75~3.50	0.5,1,2,5,4,5,6,7,8,9,10,11	75	14/16/18	INB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to	-9.00	0.75~3.50	2,25,4,25,6,25,8,25	76	14/16/18	INF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	70	14/16/18	INS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		0.75~3.50	6,8	75	14/16/18	INO

* The true base curve will be selected by an Index of material