

DIO OPTIMA

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+11.25	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,12	75	14/16/18/20	DIC
1.60	1.597	1.30	42	400	Clear	S+10.00	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	14/16/18/20	DIM
1.67	1.665	1.35	32	400	Clear	S+11.50	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	14/16/18/20	DIH
1.74	1.738	1.47	31	390	Clear	S+10.50	to	-12.00	0.75~3.50	0.5,1.5,3,5,5,6,7,8,8.5,10,25,12.5	75	14/16/18/20	DIU
TVX	1.530	1.11	45	400	Clear	S+7.00	to	-10.50	0.75~3.50	0.5,1,2,2.5,3,4,5,6,7,8	75	14/16/18/20	DIV
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to	-11.00	0.75~3.50	1,2,5,4,5,6,7,8,9,10,11	75	14/16/18/20	DI3
Polycarbonate	1.586	1.17	31	380	Clear		to		0.75~3.50		75	14/16/18/20	DIP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	2.25,4,25,5,25,6,25,8,25	76	14/16/18/20	DIA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+9.50	to	-11.00	0.75~3.50	0.5,1,2,5,4,5,6,7,8,9,10,11	75	14/16/18/20	DIB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to	-9.00	0.75~3.50	2.25,4,25,6,25,8,25	76	14/16/18/20	DFF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	70	14/16/18/20	DIS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		0.75~3.50	6,8	75	14/16/18/20	DIO
Polarized 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-9.00	0.75~3.50	2,4,6,8	75	14/16/18/20	DID
Polarized 1.6	1.594	1.30	42	400	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,6,8	75	14/16/18/20	DIE
NXT Sun	1.530	1.11	45	400	Grey/Brown/etc	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	75	14/16/18/20	DIN
NXT Polar	1.530	1.11	45	400	Grey/Brown	S+7.00	to	+0.00	0.75~3.50	6,8	75	14/16/18/20	DIN
NXT Varia	1.530	1.11	45	380	Grey/Brown/etc	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	75	14/16/18/20	DIN

* The true base curve will be selected by an Index of material