

DIO PRO

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+11.25	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,12	75	14/16/18/20	EDC
1.60	1.597	1.30	42	400	Clear	S+10.00	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	14/16/18/20	EDM
1.67	1.665	1.35	32	400	Clear	S+11.50	to	-11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	14/16/18/20	EDH
1.74	1.738	1.47	31	390	Clear	S+10.50	to	-12.00	0.75~3.50	0.5,1.5,3.5,5,6.75,8.5,10.25,12.5	75	14/16/18/20	EDU
TVX	1.530	1.11	45	400	Clear	S+7.00	to	-10.50	0.75~3.50	0.5,1,2,2.5,3,4,5,6,7,8	75	14/16/18/20	EDV
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to	-11.00	0.75~3.50	1,2,5,4,5,6,7,8,9,10,11	75	14/16/18/20	ED3
Polycarbonate	1.586	1.17	31	380	Clear		to		0.75~3.50		75	14/16/18/20	EDP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	2.25,4.25,5.25,6.25,8.25	76	14/16/18/20	EDA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+9.50	to	-11.00	0.75~3.50	0.5,1,2,5,4,5,6,7,8,9,10,11	75	14/16/18/20	EDB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to	-9.00	0.75~3.50	2.25,4.25,6.25,8.25	76	14/16/18/20	EFF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	70	14/16/18/20	EDS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		0.75~3.50	6,8	75	14/16/18/20	EDO
Polarized 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-9.00	0.75~3.50	2,4,6,8	75	14/16/18/20	EDD
Polarized 1.6	1.594	1.30	42	400	Grey/Brown	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,6,8	75	14/16/18/20	EDE
NXT Sun	1.530	1.11	45	400	Grey/Brown/etc	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	75	14/16/18/20	EDN
NXT Polar	1.530	1.11	45	400	Grey/Brown	S+7.00	to	+0.00	0.75~3.50	6,8	75	14/16/18/20	EDN
NXT Varia	1.530	1.11	45	380	Grey/Brown/etc	S+7.00	to	-11.00	0.75~3.50	0.5,2,4,5,6,8	75	14/16/18/20	EDN

* The true base curve will be selected by an Index of material