

# DIO SPORTS ATOR

## Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Nominal Base Curve	Effective Max DIA	ID mark
1.50	1.498	1.32	58	350	Clear	S+4.25	to	-4.50	6/8	80	-
1.60	1.597	1.30	42	400	Clear	S+5.50	to	-4.75	6/8	80	-
1.67	1.665	1.35	32	400	Clear	S+5.50	to	-5.00	6/8	80	-
Polycarbonate	1.586	1.17	31	380	Clear		to		6/8	75	-
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+4.50	to	-3.00	6/8	76	-
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+5.50	to	-4.50	6/8	75	-
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+4.00	to	-5.00	6/8	76	-
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+4.50	to	-3.00	8	70	-
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		6/8	75	-
Polarized 1.5	1.498	1.32	58	350	Grey/Brown	S+4.50	to	-5.50	6/8	75	-
Polarized 1.6	1.594	1.30	42	400	Grey/Brown	S+4.75	to	-2.25	8	75	-
NXT Sun	1.530	1.11	45	400	Grey/Brown/etc	S+4.50	to	-2.00	6/8	80	-
NXT Polar	1.530	1.11	45	400	Grey/Brown	S+5.00	to	-5.00	6/8	75	-
NXT Varia	1.530	1.11	45	380	Grey/Brown/etc	S+5.00	to	-5.00	6/8	80	-
NXT Varia Polar	1.530	1.11	45	400	Grey	S+5.00	to	-5.00	6/8	75	-

\* The true base curve will be selected by an Index of material